

TEXTAC II

ADHESIVE

PROPERTIES:

- Appearance: White liquid, dries clear
- Solids: 58 - 60% by wt.
- Viscosity: 2,400-3,000 cps (LFV 46077)
- Shelf Life: 1 year min. at room temp.
- pH: 4.5 - 5.5
- Wt. per gallon: 8.45 lbs.
- Flammable: No
- Freeze/Thaw Stable: No

APPLICATIONS:

- Garment hold down for printing
- Ideal for thick garments such as fleece and sweatshirts
- Ideal for smooth fabrics such as nylon and polyester

INSTRUCTIONS:

Apply: TextTac II can be applied to pallet manually with a card, paintbrush, or spray bottle. We recommend air assisted spray units for fine, even coatings. We suggest applying pallet tape to a clean surface - this avoids scrubbing TextTac II from the pallet. Only a thin layer is needed for shirt printing; however, a thicker layer is needed for fleece, sweat shirts, towels, or other high lint materials.

Dry: TextTac II can be air-dried; however, 20 seconds under a flash unit will accelerate drying. A heavier coat of adhesive increases tack strength and dry times. TextTac II will turn clear when dry.

Retack: When lint build-up diminishes tack, a damp sponge can be used to knock off lint and re-tackify the adhesive, or reapply and allow TextTac II to dry. Adhesive may transfer to garment if it is not dry or bonded to pallet. Retacking may not be necessary until 200 to 400 impressions.

Clean up: Pallets, equipment, and floors can be cleaned with hot water mixed with image mate Degreaser 260. Pallet paper eliminates pallet cleaning. Acetone may be used on stubborn areas.



Chromaline Screen Print Products
4832 Grand Ave. • Duluth, Minnesota 55807 • Tel: 218.628.2217
Fax: 218.628.3245 • Web Site: www.chromaline.com
E-mail: sales@chromaline.com

AN IKONICS COMPANY

ISO 9001 CERTIFIED

NASDAQ LISTED: IKNX



PERFORMANCE PROPERTIES:

- Greater tack strength than TextTac
- Water removable
- Non-flammable
- Will not transfer onto textile garment
- One gallon replaces 4 to 5 cases of aerosol containers

STANDARD SIZE:

- 5 Gallon

For Technical Service
Call Toll Free **1-800-328-4261**
(Outside North America Call +1-218-628-2217)
Email: help@chromaline.com